



Medium HP A3



Property	Unit	Range					
Grammage	g/m^2	AVG	100	110	120	130	140
Grammage	g/m^2	MIN/MAX	100±5	110±5	120±5	130±5	140±6
Density	g/cm^3	MIN	0.6	0.6	0.6	0.6	0.6
RCT (CD)(strength)	kgf/152mm	MIN	9.30	11.10	13.00	16.10	18.40
RCT(CD) (Index)	N.m/g	MIN	6.00	6.50	7.0	8.0	8.5
COBB60S(Top/back)	g/m^2	MAX	60	60	60	60	60
Moisture	%	AVG	8±2	8±2	8±2	8±2	8±2

Remark:

Conditions of Testing: temp 23±1°C, RH(50±2)%

Test Methods: ISO534, 535, 536, 287, 1924, 5627,2758

Guangzhou KIKO Paper Industry Co., Ltd/ KIKO (Hong Kong) Company Limited All Right Reserved