

KIKAA Kraft Liner AA



Property	Unit	Range			
Grammage	g/m^2	AVG	160	200	230
Grammage	g/m^2	MIN/MAX	160±5	200±7	230±7
Density	g/cm^3	MIN	0.7	0.7	0.7
Burst strength	kgf/cm^2	MIN	6.20	7.75	8.91
Burst Index	$kpa.m^2/g$	MIN	3.8	3.8	3.8
BF	$gf.m^2/g.cm^2$	MIN	10.0	11.0	11.0
RCT(CD)	$kgf/152mm$	MIN	24.8	34.1	39.2
RCT(CD) Index	$N.m/g$	MIN	10.0	11.0	11.0
COBB60S(Top/back)	g/m^2	MAX	40/50	40/50	40/50
Moisture	%	AVG	8±2	8±2	8±2

Remark:

Conditions of Testing: temp 23±1°C, RH(50±2)%

Test Methods: ISO534, 535, 536, 287, 1924, 5627,2758

Guangzhou KIKAA Paper Industry Co., Ltd/ KIKAA (Hong Kong) Company Limited All Right Reserved