

KIK Kraft Liner N



Property	Unit	Range									
Grammage	g/m ²	AVG	100	110	120	130	140	160	170	180	200
Grammage	g/m ²	MIN/MAX	100±5	110±5	120±5	130±5	140±5	160±5	170±5	180±5	200±6
Density	g/cm ³	MIN	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7
Burst strength	kgf/cm ²	MIN	2.45	2.69	2.94	3.18	3.43	3.92	4.16	4.22	4.69
Burst Index	kpa.m ² /g	MIN	2.40	2.40	2.40	2.40	2.40	2.40	2.40	2.30	2.30
BF	gf.m ² /g.cm ²	MIN	24.5	24.5	24.5	24.5	24.5	24.5	24.5	23.5	23.5
CMT'	N	MIN	240	264	288	312	336	384	408	414	460
	kgf	MIN	24.5	26.9	29.4	31.8	34.3	39.2	41.6	42.2	46.9
	lbf	MIN	53.9	59.3	64.7	70.1	75.5	86.3	91.7	93.0	103.4
RCT(CD)	kgf/152mm	MIN	9.30	10.74	11.72	13.10	14.10	17.36	18.44	19.53	23.25
RCT(CD) Index	N.m/g	MIN	6.0	6.3	6.3	6.5	6.5	7.0	7.0	7.0	7.5
Ring Crush	N/152mm	MIN	91	105	115	128	138	170	181	192	228
	kgf/cm	MIN	59	62	62	64	64	69	69	69	74
	kgf/6inch	MIN	894	1033	1127	1260	1357	1670	1774	1878	2236
COBB60S(Top/back)	g/m ²	MAX	70/100	70/100	70/100	70/100	70/100	70/100	70/100	70/100	70/100
Moisture	%	AVG	8±2	8±2	8±2	8±2	8±2	8±2	8±2	8±2	8±2

Remark:

Conditions of Testing: temp 23±1 °C, RH(50±2)%

Test Methods: ISO534, 535, 536, 287, 1924, 5627,2758