

KIKA Kraft Liner F



Property	Unit	Range				
Grammage	g/m^2	AVG	110	120	130	140
Grammage	g/m^2	MIN/MAX	110±4	120±5	130±5	140±5
Density	g/cm^3	MIN	0.6	0.62	0.62	0.65
Burst strength	kgf/cm^2	MIN	3.03	2.94	3.05	3.28
Burst Index	$kpa.m^2/g$	MIN	2.70	2.40	2.3	2.3
BF	$gf.m^2/g.cm^2$	MIN	27.5	24.5	23.5	23.5
RCT(CD) Index	$N.m/g$	MIN	5.5	6.0	6.2	6.6
COBB60S(Top/back)	g/m^2	MAX	22/25	22/25	22/26	23/25
Moisture	%	AVG	8±1	8±1	8±2	8±1

Remark:

Conditions of Testing: temp 23±1°C, RH(50±2)%

Test Methods: ISO534, 535, 536, 287, 1924, 5627,2758

Guangzhou KIKA Paper Industry Co., Ltd/ KIKA (Hong Kong) Company Limited All Right Reserved