

# KIKA Duplex H



Property	Unit	Range					
Grammage	g/m <sup>2</sup>	AVG	230	250	300	350	400
Grammage	g/m <sup>2</sup>	MIN/MAX	230±5%	250±5%	300±5%	350±5%	400±5%
Caliper	µm	AVG	280±15	310±15	370±15	440±15	505±15
	pt	AVG	11.0	12.2	14.5	17.3	19.9
Roughness(top)	µm	MIN	2.0	2.0	2.0	2.0	2.0
Brightness(top)	%	MIN	80.0	80.0	80.0	80.0	80.0
Gloss 75°	%	MIN	50	50	50	50	50
CD Stiffness	MN.M	MIN	1.7	2.0	4.9	5.5	8.5
MD Stiffness	MN.M	MIN	3.4	4.0	8.0	11.0	13.0
K&N Value	%	MIN/MAX	25±5	25±5	25±5	25±5	25±5
COBB60S(Top/back)	g/m <sup>2</sup>	MAX	50/150	50/150	50/150	50/150	50/150
Moisture	%	AVG	7.5±2	7.5±2	7.5±2	8.0±2	8.0±2
Dirt	Spot/m <sup>2</sup>	MAX	40	40	40	40	40

**Remark:**

Conditions of Testing: temp 23±1℃, RH(50±2)%

Test Methods: ISO534, 535, 536, 287, 1924, 5627,2758

Guangzhou KIKA Paper Industry Co., Ltd/ KIKA (Hong Kong) Company Limited All Right Reserved