

# KIKA Medium HP A7



Property	Unit	Range					
<b>Grammage</b>	$g/m^2$	AVG	110	120	130	140	180
Grammage	$g/m^2$	MIN/MAX	110±5	120±5	130±5	140±5	180±5
Density	$g/cm^3$	MIN	0.55	0.55	0.55	0.55	0.55
RCT (CD) strength	kgf/152mm	MIN	11.60	13.00	15.10	17.40	23.70
RCT(CD) Index	N.m/g	MIN	6.80	7.00	7.5	8.0	8.5
MD Breaking Length	km	MIN	3.00	3.50	4.0	4.5	4.5
COBB 60S(Top/back)	$g/m^2$	MAX	50	50	50	50	50
Moisture	%	AVG	8±2	8±2	8±2	8±2	8±2

**Remark:**

Conditions of Testing: temp 23±1°C, RH(50±2)%

Test Methods: ISO534, 535, 536, 287, 1924, 5627,2758

Guangzhou KIKA Paper Industry Co., Ltd/ KIKA (Hong Kong) Company Limited All Right Reserved