



# Medium HP A25



Property	Unit	Range				
<b>Grammage</b>	$g/m^2$	AVG	100	112	125	150
Grammage	$g/m^2$	MIN/MAX	100±4	112±4	125±4	150±4
Density	$g/cm^3$	MIN	0.5	0.5	0.5	0.5
RCT (CD) strength	kgf/152mm	MIN	10.80	13.80	17.40	23.20
RCT(CD) Index	N.m/g	MIN	7.00	8.00	9.0	10.0
COBB120S(Top/back)	$g/m^2$	MAX	45	45	45	45
Moisture	%	AVG	8±1	8±1	8±1	8±1

**Remark:**

Conditions of Testing: temp 23±1°C, RH(50±2)%

Test Methods: ISO534, 535, 536, 287, 1924, 5627,2758

Guangzhou KIK Paper Industry Co., Ltd/ KIK (Hong Kong) Company Limited All Right Reserved