

# KIKA Medium HP A22



Property	Unit	Range	80	90	100	110	120	130	140	150	170
Grammage	g/m <sup>2</sup>	AVG	80	90	100	110	120	130	140	150	170
Grammage	g/m <sup>2</sup>	MIN/MAX	80±4%	90±4%	100±4%	110±4%	120±4%	130±4%	140±4%	150±4%	170±4%
Density	g/cm <sup>3</sup>	MIN	0.5	0.5	0.5	0.5	0.5	0.50	0.5	0.5	0.5
RCT (CD) strength	kgf/152mm	MIN	6.20	8.09	10.10	11.90	13.4	15.10	16.90	19.3	23.7
RCT(CD) Index	N.m/g	MIN	5.0	5.8	6.5	7.0	7.2	7.5	7.8	8.3	9.0
MD Breaking Length	km	MIN	4.30	4.3	4.30	4.30	4.3	4.3	4.3	4.3	4.3
COBB 60S(Top/back)	g/m <sup>2</sup>	MAX	40	40	40	40	40	40	40	40	40
Moisture	%	AVG	8±2	8±2	8±2	8±2	8±2	8±2	8±2	8±2	8±2

**Remark:**

Conditions of Testing: temp 23±1°C, RH(50±2)%

Test Methods: ISO534, 535, 536, 287, 1924, 5627,2758

Guangzhou KIKA Paper Industry Co., Ltd/ KIKA (Hong Kong) Company Limited All Right Reserved