

KIK Kraft Liner Q2



| Property | Unit | Range | | | | | | | |
|-------------------|--------------------------------------|---------|--------|--------|--------|--------|--------|--------|--------|
| Grammage | g/m ² | AVG | 100 | 110 | 120 | 130 | 140 | 160 | 170 |
| Grammage | g/m ² | MIN/MAX | 100±5 | 110±5 | 120±5 | 130±5 | 140±5 | 160±5 | 170±6 |
| Density | g/cm ³ | MIN | 0.7 | 0.7 | 0.7 | 0.7 | 0.7 | 0.7 | 0.7 |
| Burst strength | kgf/cm ² | MIN | 2.45 | 2.69 | 2.94 | 3.05 | 3.28 | 3.75 | 3.99 |
| Burst Index | kpa.m ² /g | MIN | 2.40 | 2.40 | 2.40 | 2.30 | 2.30 | 2.30 | 2.30 |
| BF | gf.m ² /g.cm ² | MIN | 24.5 | 24.5 | 24.5 | 23.5 | 23.5 | 23.5 | 23.5 |
| RCT(CD) | kgf/152mm | MIN | 9.3 | 11.1 | 13.2 | 14.9 | 16.7 | 58.2 | 61.8 |
| RCT(CD) Index | N.m/g | MIN | 6.0 | 6.5 | 7.1 | 7.4 | 7.7 | 19.8 | 22.4 |
| COBB60S(Top/back) | g/m ² | MAX | 60/100 | 60/100 | 60/100 | 60/100 | 60/100 | 60/100 | 60/100 |
| Moisture | % | AVG | 8±2 | 8±2 | 8±2 | 8±2 | 8±2 | 8±2 | 8±2 |

Remark:

Conditions of Testing: temp 23±1°C, RH(50±2)%

Test Methods: ISO534, 535, 536, 287, 1924, 5627, 2758

Guangzhou KIK Paper Industry Co., Ltd/ KIK (Hong Kong) Company Limited All Right Reserved