

# KIKA WTL(Uncoated) S2



Property	Unit	Range			
<b>Grammage</b>	$\text{g/m}^2$	AVG	140	170	200
Grammage	$\text{g/m}^2$	MIN/MAX	140±4	170±4	200±4
Density	$\text{g/cm}^3$	MIN	0.8	0.8	0.8
Smoothness(top)	$\mu\text{m}$	MAX	7	7	7
Brightness(top)	%	MIN	82	82	75
Burst Index	$\text{kpa.m}^2/\text{g}$	MIN	2.3±5%	2.3±5%	2.3±5%
CD Folding Endurance	times	MIN	30	30	30
Ply Bonding Strength	$\text{J/m}^2$	MIN	250	250	250
COBB 120S(Top/back)	$\text{g/m}^2$	MAX	80/120	80/120	80/120
Moisture	%	AVG	8±2	8±2	8±2
Dirt	$\text{Spot/m}^2$	MAX	80	80	80

**Remark:**

Conditions of Testing: temp 23±1°C, RH(50±2)%

Test Methods: ISO534, 535, 536, 287, 1924, 5627,2758

Guangzhou KIKA Paper Industry Co., Ltd/ KIKA (Hong Kong) Company Limited All Right Reserved