

KIKA WTL(Coated) J



Property	Unit	Range			
Grammage	g/m ²	AVG	150	170	200
Grammage	g/m ²	MIN/MAX	150±5	170±6	200±7
Density	g/cm ³	MIN	0.9	0.9	0.9
Roughness	μm	MAX	2	2	2
Brightness(top)	%	MIN	82±2	82±2	82±2
Burst Index	kpa.m ² /g	MIN	2.3	2.3	2.3
CD Folding Endurance	times	MIN	30.0	30.0	30.0
Ply Bonding Strength	J/m ²	MIN	160	160	160
COBB60S(Top/back)	g/m ²	MAX	50/100	50/100	50/100
Moisture	%	AVG	8±2	8±2	8±2
K&N Value(Top)	%	AVG	25±2	25±2	25±2
Dirt	Spot/m ²	MAX	80	80	80

Remark:

Conditions of Testing: temp 23±1°C, RH(50±2)%

Test Methods: ISO534, 535, 536, 287, 1924, 5627,2758

Guangzhou KIKA Paper Industry Co., Ltd/ KIKA (Hong Kong) Company Limited All Right Reserved

